

ABSTRACT OF THE DISCLOSURE

A metal master having higher shape precision than conventional ones and a method for manufacturing such metal master are provided. The metal master has a conductive film having a thickness of about 50 nm (that is within a range of 35 to 200 nm).